

none



none



INVESTOR IN PEOPLE

PN - EP0065207 A 19821124
 PD - 1982-11-24
 PR - DE19813118256 19810508
 OPD - 1981-05-08
 TI - Use of pigmented coating compounds with reduced emission capability in the spectral range of the heat radiation for camouflage purposes.
 AB - 1. Use of pigmented coating compounds with reduced emission capability in the spectral range of heat radiation and with differing colour properties, which contain 1 to 70% by weight of aluminium metal pigment, for infrared camouflage purposes.
 N - HEUEL MEINOLF DIPL-PHYSKURTH HERBERT; FALLER FRITZ; GANSON GERTRAUD; SELDERS MATHIAS DR; TSCHULENA GUIDO DR
 PA - HERBERTS & CO GMBH (DE)
 EC - C09D5/30 ; C09D5/38 ; B05D5/00+B ; B05D5/06+B
 IC - C09D5/38 ; B05D5/00
 CT - US4289677 A [XP]; US4011190 A [X]; AT357248B B [X]

© WPI / DERWENT

TI - Pigmented paint with low thermal radiation emission - contg. metal pigment with high electroconductivity, pref. in flake, rod-like or spherical form
 PR - DE19813118256 19810508
 PN - EP0065207 A 19821124 DW198248 Ger 012pp
 - DE3118256 A 19821202 DW198249 000pp
 - EP0065207 B 19850807 DW198532 Ger 000pp
 PA - (BATT) BATTELLE-INST EV
 - (HERK) HERBERTS GMBH
 IC - B05D5/00 ; C09D5/38
 IN - FALLER F; GANSON G; HEUEL M; KURTH H; SELDERS M; TSCHULENA G
 AB - EP--65207 Pigmented paint with low emission power in the spectral region of thermal radiation and in different colour properties contains 1-70 (3-30) wt.% metal pigment (I) with high electroconductivity. The paint is useful for solar collectors, for reducing energy losses from hot pipes, for reflecting heat from the walls behind heaters, for making, e.g. in IR test equipment, and as military IR camouflage paint. It combines low IR emission with the

X:1

none

none

none

other normal properties, e.g. shade, abrasion resistance, corrosion protection etc.

- Pref. (I) is in the form of rodlets, spheres or esp. flakes and consists of Zn, gold bronze, Sn or esp. Al. Its dimensions are 0.1-100 microns, with a large dia./thickness ratio flake and a large dia./length ratio for rodlets. Flakes with a dia. of 5-20 (10) microns are used for grey shades and with a dia. of 10-80 (40-50) microns for light shades, their thickness being 0.1-10 (1) microns.

EPAB - EP--65207 Pigmented paint with low emission power in the spectral region of thermal radiation and in different colour properties contains 1-70 (3-30) wt.% metal pigment (I) with high electroconductivity. The paint is useful for solar collectors, for reducing energy losses from hot pipes, for reflecting heat from the walls behind heaters, for making, e.g. in IR test equipment, and as military IR camouflage paint. It combines low IR emission with the other normal properties, e.g. shade, abrasion resistance, corrosion protection etc.

- Pref. (I) is in the form of rodlets, spheres or esp. flakes and consists of Zn, gold bronze, Sn or esp. Al. Its dimensions are 0.1-100 microns, with a large dia./thickness ratio flake and a large dia./length ratio for rodlets. Flakes with a dia. of 5-20 (10) microns are used for grey shades and with a dia. of 10-80 (40-50) microns for light shades, their thickness being 0.1-10 (1) microns. (12pp)

OPD - 1981-05-08

CT - AT357248;US4011190;US4289677

DS - AT BE CH FR GB IT LI NL SE

AN - 1982-02581J [48]